

Amendments to the Claims

1. **(Currently amended)** A polyolefin resin molding composite comprising
~~a surface layer and a foam layer,~~ or a surface layer, a foam layer, and a base member,
the foam layer being produced by fusion bonding thermoplastic expanded resin
particles to one another by molding, the thermoplastic expanded resin particles comprising
a core that is made of a crystalline thermoplastic resin and is in an expanded state, and a
polyethylene resin coat covering the core that is in a substantially non-expanded state,
wherein the foam layer has a compressive hardness of from 0.05 to 0.7 MPa; and
the surface layer comprising a thermoplastic synthetic resin having a melting point
of 5°C or more higher than a melting point of the polyethylene resin constituting the coat
of the particles;
wherein the surface layer is fusion bonded directly to the foam layer, and
wherein the base member is fusion bonded directly to the foam layer.

2. **(Cancelled)**

² ~~3.~~ **(Previously presented)** The polyolefin resin molding composite according to claim 1,
wherein the polyethylene resin coat comprises an ethylene polymer having a melting point lower
than the crystalline thermoplastic resin constituting the core, or an ethylene polymer that
substantially exhibits no melting point.

4. **(Cancelled)**

³ ~~5.~~ **(Previously presented)** The polyolefin resin molding composite according to claim ~~3~~,
wherein a void fraction of the foam layer is 1 to 40 %.

4 ~~6.~~ (Previously presented) The polyolefin resin molding composite according to claim ~~3~~², wherein the thermoplastic synthetic resin constituting the surface layer is a polyolefin resin.

7-9. (Cancelled)

5 ~~10.~~ (New) The polyolefin resin molding composite according to claim 1, wherein the surface layer is fusibly bonded to the coat of the expanded resin particles which constitute the foam layer.